

5. FIRE FIGHTING MEASURES

Flash Point (°F/C):	More than 200 degrees F. Method: Tag Closed Cup
Recommended Extinguishing Media:	Carbon Dioxide, Dry Chemicals, Foam.
Special Fire-Fighting Procedures:	Water spray may be ineffective on flames but should be used to keep fire-exposed containers cool.
Hazardous Products of Combustion:	Acetic acid, Formaldehyde, Silica fume, Oxides of nitrogen, Oxides of carbon, Oxides of sulfur, Metal oxide fumes
Unusual Fire/Explosion Hazards:	None
Lower Explosive Limit:	Acetic acid: 4%
Upper Explosive Limit:	Acetic acid: 19.9% @ 200 degrees F.

6. ACCIDENTAL RELEASE MEASURES

Spill Procedures:	Wipe or scrape up spill material. Maintain good ventilation for large spills. Place scrap material in a well-ventilated area and allow to cure to rubber. Clean up spills thoroughly as residue is slippery.
--------------------------	--

7. HANDLING AND STORAGE

Storage:	Store away from water or moisture Keep away from oxidizers.
Handling:	Avoid contact with skin and eyes. Do not wear contact lenses. Use only in a well ventilated area. Do not take internally.

8. EXPOSURE CONTROLS/PERSONAL PROTECTION

Eyes:	Safety glasses.
Skin:	Neoprene, rubber or butyl rubber gloves.
Ventilation:	General ventilation is usually adequate.
Respiratory Protection:	Not required under normal use. An approved respirator (i.e. NIOSH, etc.) should be worn when exposures are expected to exceed the applicable limits.

Comments:	When heated to temperatures above 300 degrees F. in the presence of air, this product can form formaldehyde vapors. Formaldehyde is a potential cancer hazard and a known skin and respiratory sensitizer. Safe handling conditions may be maintained by keeping vapor concentrations below the OSHA permissible limit for formaldehyde.
------------------	--

9. PHYSICAL AND CHEMICAL PROPERTIES

Appearance:	Red paste
Odor:	Acetic acid
Boiling Point:	Not applicable, polymeric material
pH:	Does not apply
Solubility in Water:	Polymerized
Specific Gravity:	1.0
VOC Content(Wt.%):	4.8% by weight; 0.42 lb/gal; 50.48 g/l
Vapor Pressure:	10 mm Hg @ 80 degrees F.
Vapor Density (Air=1):	Not Determined
Evaporation Rate:	Not Determined

10. STABILITY AND REACTIVITY

Chemical Stability:	Stable at normal conditions
Hazardous Polymerization:	Will not occur
Incompatibilities:	Polymerized by contact with moisture. Acetic acid liberated.
Conditions to Avoid:	Exposure to moisture
Hazardous Products of Combustion:	Acetic acid. Formaldehyde. Silica fume. Oxides of nitrogen. Oxides of carbon. Oxides of sulfur. Metal oxide fumes.

11. TOXICOLOGICAL INFORMATION

See Section 3

12. ECOLOGICAL INFORMATION

No data available

13. DISPOSAL CONSIDERATIONS

Recommended Method of Disposal: Disposal should be made in accordance with federal, state and local regulations.

Product name: 26C HIGH TEMP RED RTV SILICONE
GASKET MAKER 11OZ

Item No: 81409

US EPA Waste Number: NH - Not a RCRA Hazardous Waste Material

14. TRANSPORTATION INFORMATION

DOT (49CFR 172)

Domestic Ground Transport

DOT Shipping Name: Unrestricted
Hazard Class: None
UN/ID Number: None
Marine Pollutant: None

IATA

Proper Shipping Name: Not regulated
Class or Division: None
UN/NA Number: None

IMDG

Proper Shipping: Unrestricted
Hazard Class: None
UN Number: None

15. REGULATORY INFORMATION

SARA 313 Chemicals: The following component(s) is listed as a SARA Section 313 Toxic Chemical.

SARA 313 Information
NONE

CALIFORNIA PROP 65:

No California Prop 65 chemicals are known to be present at or above the No Significant Risk Level.

TSCA Inventory Status:

Listed on Inventory: **YES** All components of this product are listed (or exempt) on the EPA TSCA inventory.

16. OTHER INFORMATION

Estimated NFPA Rating: HEALTH 2, FLAMMABILITY 1, REACTIVITY 0

Estimated HMIS Classification: HEALTH 2, FLAMMABILITY 1, PHYSICAL HAZARD 0

NFPA is a registered trademark of the National Fire Protection Assn.

HMIS is a registered trademark of the National Paint and Coatings Assn.

Prepared By: Denise Boyd, Health and Safety Manager
Company: Permatex, Inc. 10 Columbus Blvd. Hartford, CT USA
06106

Revision Date: 08/08/2005
Revision 5
Number:

Telephone No.: 1-87-Permatex (877) 376-2839